

LUCENE™ LC100

Polyolefin Elastomer

Applications

- General purpose thermoplastic elastomer for polymer modification
- Shoe sole, Wire & Cable, Packaging Films

Description

- LUCENE™ LC100 is an ethylene-1-octene copolymer produced using LG Chem's metallocene polymerization catalyst and solution process technology.
- LUCENE™ LC100 is an excellent impact modifier for plastics and offers unique performance capabilities for compounded products.
- LUCENE™ LC100 complies with FDA regulation 21 CFR 177.1520(c)(3.2c).

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
Density	ASTM D1505	g/cm ³	0.903
MFR(190°C,2.16kg)	ASTM D1238	g/10min	1.2
Mooney Viscosity(ML1+4@121°C)	ASTM D1646	MU	23
Mechanical⁽²⁾			
Tensile Strength at Break	ASTM D638 ⁽³⁾	Mpa	38
Elongation at Break	ASTM D638 ⁽³⁾	%	660
Tear Strength	ASTM D624	kN/m	87
Flexural Modulus 1% Secant	ASTM D790	Mpa	83
Hardness			
Shore hardness(Shore A)	ASTM D2240	-	91
Thermal			
Melting Temperature	LG	°C	96
Glass Transition Temperature	LG	°C	-31

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 500 mm/min.

Processing information

- LUCENE™ LC100 may be processed on conventional equipment. It is recommended that hopper feed throat should be cooled below 30°C to prevent from pellet bridging with low melting point .

For additional sales, order and technical assistance

Revised :11/07/2014

Head office PO Division, LG Chem Ltd.
Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-6734

TS&D **TECH Center. Polyolefin**
175, Gajeong-ro, Yuseong-gu, Daejeon, 305-343, Korea.
Tel. 82-42-860-8341

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."